



Toyo Seiki Seisaku-sho, Ltd. 5-15-4, Takinogawa, Kita-ku, Tokyo 114-8557, Japan

No. 613 Dart Impact Tester



■ APPLICATION

The **Dart Impact Tester** evaluates impact rupture strength by measuring impact energy applied to plastic films.

■ SPECIFICATIONS

Dart	Method A <ul style="list-style-type: none"> ■ Aluminum dart: Ø1.5" (38.0mm), 32g ■ Epoxy dart: Ø1.5" (38.0mm), 32g Method B <ul style="list-style-type: none"> ■ Stainless steel dart: Ø2.0" (50.8mm), 320g
Weight	Method A <ul style="list-style-type: none"> ■ 5g (x2) ■ 15g (x8) ■ 30g (x8) ■ 60g (x8) ■ 120g (x1) Method B <ul style="list-style-type: none"> ■ 15g (x2) ■ 45g (x8) ■ 90g (x8) ■ 180g (x1)
Falling height	250 to 1520mm
Compressed air required	0.5MPa
Dimensions	W1050 x D575 x H2480mm
Weight	Approx. 97kg
Related standards	ISO 7765-1 JIS K 7124-1 ASTM D 1709

■ OPTION

	Name	Model
1	Safety cover	

Specifications are subject to change without notice.

TOYOSEIKI

TOYO SEIKI SEISAKU-SHO, LTD.

5-15-4, Takinogawa, Kita-ku, Tokyo 114-8557, Japan

Tel:+81-3-3916-8183 Fax:+81-3-3916-8173

www.toyoseiki.co.jp

20191205 MN